

*1. Unique identification code of the product-type:*

**Aggregates**

*2. Type, batch or serial number or any other element allowing identification of the construction product as required pursuant to Article 11(4):*

**Stainton 4-20mm**

*3. Intended use or uses of the construction product, in accordance with the applicable designated technical specification, as foreseen by the manufacturer:*

**Preparation of concrete for use in Buildings, roads and other civil engineering works.**

*4. Name, registered trade name or registered trade mark and contact address of the manufacturer as required pursuant to Article 11(5):*

**Stainton Quarry, Ruddell Mill Lane, Stainton, Maltby, South Yorkshire, S66 7RH**

*5. Where applicable, name and contact address of the authorised representative whose mandate covers the tasks specified in Article 12(2):*

**Not applicable**

*6. System or systems of assessment and verification of constancy of performance of the construction product as set out in Annex V:*

**System 4**

*7. In case of the declaration of performance concerning a construction product covered by a designated standard:*

**BS EN 12620:2002 +A1:2008**

*8. In case of the declaration of performance concerning a construction product for which a UK Assessment Document has been issued:*

**Not applicable**

## GB Declaration of Performance: S-02



Marshall's Mono Ltd, Landscape House, Lowfields Business Park, Elland, West Yorkshire HX5 9HT

Registered in England: 509579

### 9. Declared performance

Essential Characteristics	Performance	Relevant Clause of BS EN 12620:2013
Particle Grading	4/10mm	4.3.1
Particle Shape	Angular to Sub-angular	4.4
Particle Density	2.85 Mg/m <sup>3</sup>	5.5
Filler Aggregate	2.61 Mg/m <sup>3</sup>	4.6
Particle Density & Water Absorption	5.3%	5.5
Resistance Fragmentation/Crushing	34	5.2
Resistance to wear	25	5.3
Resistance to Polishing	56	5.4
Resistance to surface abrasion	16	5.4.2
Petrographic Description	Dolomite	8.1
Chlorides	0.001%	6.2
Acid Soluble Sulphates	<0.1%	6.3
Total Sulphur	<0.1%	6.3
Influence on initial setting time of cement	NPD	6.4.1
Calcium Carbonate Content (For concrete pavement surfaces)	NPD	6.2
Volume Stability (drying Shrinkage)	0.062%	5.7.2
Water Absorption	5.3%	5.5
Dangerous Substances	NPD	H.3.3 H.4
Durability against Freeze Thaw Resistance	1.0%	5.7.1
Durability against Alkali Silica reactivity	5.44(mmols/l) 9.09 (mmols/l)	5.7.3

Where pursuant to Article 37 or 38 the Specific Technical Documentation has been used, the requirements with which the product complies:

### Not applicable

10. The performance of the product identified in points 1 and 2 is in conformity with the declared performance in point 9.

This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, As it has effect in the United Kingdom" under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

Simon Bourne

Chief Commercial Officer

*Celtest report reference 116692*

Date: 24<sup>th</sup> July 2025

Place of Issue: Elland, Halifax, UK